

Synchrotron radiation micro-computed tomography for the investigation of finishing treatments in historical bowed string instruments: Issues and perspectives^{* **}

Giacomo Fiocco^{1,2}, Tommaso Rovetta^{1,3}, Marco Malagodi^{1,4}, Maurizio Licchelli¹, Monica Gulmini^{2,a}, Gabriele Lanzafame⁵, Franco Zanini⁵, Alessandro Lo Giudice⁶, and Alessandro Re⁶

¹ Laboratorio Arvedi di Diagnostica Non Invasiva, CISRiC, Università degli Studi di Pavia, Via Bell'Aspa 3, 26100 Cremona, Italy

² Dipartimento di Chimica, Università di Torino, Via Pietro Giuria 5, 10125. Torino, Italy

³ Dipartimento di Fisica, Università degli Studi di Pavia, Via Bassi 6, 27100 Pavia, Italy

⁴ Dipartimento di Musicologia e Beni Culturali, Corso Garibaldi 178, 26100 Cremona, Italy

⁵ Elettra-Sincrotrone Trieste S.C.p.A., S.S. 14 km 163.5, 34194 Basovizza, Trieste, Italy

⁶ Dipartimento di Fisica, Università di Torino and INFN, Sezione di Torino, Via Pietro Giuria 1, 10125 Torino, Italy

Received: 21 June 2018 / Revised: 14 September 2018

Published online: 19 December 2018

© Società Italiana di Fisica / Springer-Verlag GmbH Germany, part of Springer Nature, 2018

Abstract. Coating systems in historical bowed string instruments are often multi-layered structures, where several inorganic and organic materials are variously combined. The methods to characterise such complex systems normally require samples to be detached from the artwork, whereas Synchrotron Radiation micro-Computed Tomography (SR-micro-CT) may reveal—through a non-invasive approach—procedures and materials employed by the ancient violin makers. Since the application of SR-micro-CT for the investigation of the finishing layers in historical bowed string instruments is still unexplored, the experimental settings were optimized for the detection of the main features expected in the finishing layers of a historical instrument. In this work, two sets of mock-ups mimicking the finishing layers of historical instruments and a large fragment removed from a damaged cello by Andrea Guarneri were scanned. By considering SR-micro-CT data, and data obtained by previous micro-invasive analyses, the merits of reconstructed volumes and virtual slicing in investigating the layered structures have been highlighted and discussed. The developed procedures enabled the detection of the main morphological features of the overlapping layers, producing a valuable, non-invasive insight into the structure of the coating systems.

1 Introduction

The smooth and shiny varnish of a historical violin is the most perceivable portion of a complex multi-layered coating system, which may contain a variety of inorganic and organic materials [1]. All these materials are involved in the finishing treatments of the musical instrument, enhancing the aesthetic features of the wood, protecting the object from wear and influencing the tonal features of the sound [2].

Nowadays, scientific investigation represents a powerful tool to rediscover the lost materials and methods adopted in the finishing treatments employed by early masters of violin making, which were traditionally passed down orally to apprentices, and forgotten when the workshop's activity ceased. Scientists have invested effort in setting up new analytical schemes and innovative techniques and procedures for probing the instruments, in order to obtain relevant information for properly identifying the context of production [3–5]. The main focus has been the characterization of the Cremonese varnish and of the other materials involved in the finishing treatments [6]. However, the in-depth coating

* Focus Point on “Past and Present: Recent Advances in the Investigation of Ancient Materials by Means of Scientific Instrumental Techniques” edited by M. Aceto, C. Grifa, C. Lubritto

** Supplementary material in the form of a .pdf file and a .mp4 file available from the Journal web page at <https://doi.org/10.1140/epjp/i2018-12366-5>

^a e-mail: monica.gulmini@unito.it (corresponding author)